



MOSCONI s.r.l.



TECHNICAL DATA SHEET

INSULATING AGGREGATE 0-6

| | | |
|---|--|--|
| Max. service temperature | °C | 900 |
| Bulk density | Kg/m ³ | 360 |
| Chemical Analysis | SiO ₂ % Al ₂ O ₃ % TiO ₂ % Fe ₂ O ₃ % | 65,0 16,0 0,5 4,0 |
| Thermal conductivity BS 1902 Section 5.5 1991 | 200°C W/m ² K 400°C W/m ² K 600°C W/m ² K | 0,11 0,12 0,13 |
| Grain size % by weight passing ISO sieves | > 6 mm % 3-6 mm % 1-3 mm % < 1 mm % | 5 15 35 45 |
| Packing | Bags (50 dm ³) kg big bags (1,0 m ³) kg | 18 360 |

Issued: January 2016

The above-mentioned data, resulting from our testings, are given as an indication of typical values.
No guarantee can be granted regarding their absolute values or working performances.